

PERFORMANCE PROPERTIES OF CORIAN®

Property	Typical Result	Test
Tensile Strength	6,000 psi	ASTM D 638
Tensile Modulus	1.5 x 10 ⁶ psi	ASTM D 638
Tensile Elongation	0.4% min.	ASTM D 638
Flexural Strength	10,000 psi	ASTM D 790
Flexural Modulus	1.2 x 10 ⁶ psi	ASTM D 790
Hardness	>85	Rockwell "M" Scale ASTM D 785
	56	Barcol Impressor ASTM D 2583
Thermal Expansion	3.02 x 10 ⁻⁵ in./in./°C (1.80 x 10 ⁻⁵ in./in./°F)	ASTM D 696
Gloss (60° Gardner)	5–75 (matte—highly polished)	ANSI Z124
Light Resistance (Xenon Arc)	No effect	NEMA LD 3-2000 Method 3.3
Wear and Cleanability	Passes	ANSI Z124.3 & Z124.6
Stain Resistance: Sheets	Passes	ANSI Z124.3 & Z124.6
Fungus and Bacteria Resistance	Does not support microbial growth	ASTM G 21 & G 22
Boiling Water Resistance	No visible change	NEMA LD 3-2000 Method 3.5
High Temperature Resistance	No change	NEMA LD 3-2000 Method 3.6
Izod Impact (Notched Specimen)	0.28 ft.-lbs./in. of notch	ASTM D 256 (Method A)
Ball Impact Resistance: Sheets	No fracture—1/2 lb. ball: 1/4" slab—36" drop 1/2"† slab—144" drop	NEMA LD 3-2000 Method 3.8
Weatherability	ΔE* ₉₄ <5 in 1,000 hrs.	ASTM G 155
Specific Gravity†	1.7	
Water Absorption	Long-term	ASTM D 570
	0.4% (3/4")	
	0.6% (1/2"†)	
	0.8% (1/4")	
Toxicity	99 (solid colors)	Pittsburgh Protocol Test ("LC ₅₀ " Test)
	66 (patterned colors)	
Flammability	All colors (Class I and Class A)	ASTM E 84, NFPA 255 & UL 723
	Flame Spread Index	
	<25	
	Smoke Developed Index	
	<25	

†Approximate weight per square foot 1/4" (6 mm) 2.2 lbs. • 1/2" (12.3 mm) 4.4 lbs.

Shapes meet or exceed the ANSI Z124.3 and ANSI Z124.6 standards for plastic sinks and lavatories.

NEMA results based on the NEMA LD 3-2000

C950-K03158-15 1/04

The information contained in this Technical Bulletin is given by E.I. du Pont de Nemours and Company free of charge. It is based on technical data which DuPont believes to be reliable and is intended for use by persons having knowledge of this technical area at their own discretion and risk. Seller assumes no responsibility for results obtained or damage incurred from the use of this Technical Bulletin either in whole or in part by a buyer of Corian®. Corian® is a DuPont registered trademark for its solid surfaces. Only DuPont makes Corian®. Copyright © 2004 E.I. du Pont de Nemours and Company. Printed in the U.S.A.

DuPont™
CORIAN®
SOLID SURFACES



The miracles of science™